

Chevaline B & B Lacquer

Purpose & Areas Of Use:

A clear protective coating for brass, bronze and copper surfaces.

Product:

A single component, clear, solvent borne acrylic coating.

Process Compatibility:

Normally used as a two coat brush applied, or three coat spray applied system. May also be used as a primer for copper and copper alloy surfaces.

Colour:

Water white, both liquid and dry film.

Standard Pack:

1 litre, 4 litre and 20 litre metal containers

Physical Properties:

Liquid Material:

Solids (% by volume): 10 +1

Solids (% by volume)

(brush grade): 12-13

Specific Gravity: 0.96-0.98

Flash Point: 32°C

Shelf Life: 3 years in original sealed containers stored in cool, dry conditions.

Applied Film:

Flexibility: Passes 3mm mandrel

Durability: Excellent weathering and very good abrasion resistance.

Chemical Resistance: Fair

Solvent Resistance: Poor

Surface Preparation:

Surfaces to be coated must be high pressure fresh water washed and it must be ensured that any grease or oil deposits are removed. Remove all stains by using a light abrasive pad and finally cleaning with a lint-free cloth. Once clean do not handle the surface with bare hands prior to B & B Lacquer application. Ensure all surfaces are dry prior to application.

Application Method:

Brush: For small areas only such as touch up and when used as a primer.

Airless Spray: For all other areas. Use 0.25-0.35mm (9-13thou) tip.

Thinning: Not generally required. If it is, thin sparingly with B&B Lacquer Thinners.

Mix thoroughly with flat bladed stirrer before and during application.

Application Properties:

Spreading Rate:

Brush Grade: 4.5-5.0sqm/litre total
(Two coats at 9-10sqm/litre/coat)

Spraying Grade: 3.5-4sqm/litre total
(Three coats at 11-12sqm/litre/coat)

Note: Avoid application in humid or cold conditions as blushing may occur during the drying process. If humidity is present ensure good airflow during application and drying periods.

Dry Time: Touch dry 10-20 minutes
Dry to recoat 30-60 minutes
System: Allow 48 hours after application of final coat for full cure to occur.

Drying times determined at 23° ± 2°C and 50% Relative Humidity.

Health & Safety:

Chevaline B&B Lacquer is solvent borne and classified Dangerous Goods Class 3. Packing Group II (UN1866) for transport and storage purposes and must be handled and stored accordingly.

Normal safety precautions must be observed at all times when using the product. No smoking in the area. Containers always securely sealed except when in use. Wear barrier cream, gloves, protective clothing and safety goggles together with a solvent cartridge respirator when working in confined area or spraying. Maintain adequate ventilation at all times during application and drying.

Equus Industries Ltd
PO Box 497 Frankston
Victoria 3199, Australia
Phone: 03 9706 6226 Fax 03 9706 4880
Email: tech-support@equus.com.au
Web: www.equus.com.au