

# Chevaline Clearcure

## Interior/exterior varnish

### Areas Of Use:

An interior/exterior varnish for all timber and timber product surfaces including walls, furniture and flooring with excellent resistance to chemicals, abrasion and ease of cleaning properties.

### Product:

A single component moisture-curing aliphatic clear polyurethane coating, stabilised for exterior durability. Available in high-solids and brush grades.

### Compatibility:

Normally used alone as a timber varnish, but can be used as a clear chemical and graffiti-resistant overglaze for **Chevaline** materials including:

**Arcutexx    Spraytexx    Troweltexx**  
**Covertexx    Coverall    Colourglaze**

In various system combinations.

### Standard Pack:

1 litre metal can, 4 litre metal can.

### Physical Properties:

<b>Liquid Material :</b>	<b>High Solids Grade</b>	<b>Brush Grade</b>
Solids (% by weight):	55%	33%
Specific Gravity:	1.04	0.99
Flash Point:	32°C	32°C
Shelf Life:	At least 12 months in original sealed containers when stored in cool dry conditions.	

### Applied Film:

**Flexibility:** Passes 3mm mandrel at 75 microm.f.t.

**Durability:** Excellent UV and weather resistance.

**Adhesion:** Very good - easily recoated.

**Chemical resistance:** Excellent resistance to acids, alkalis, solvents, fuels, cleaning compounds.

**Abrasion resistance:** Excellent - very suitable for flooring in heavy use areas.

### Surface Preparation:

**Timber and timber products:** All surfaces must be clean and dry at time of coating. Rough surfaces should be sanded smooth and imperfections and fastener holes filled with a polyester or polyurethane filler.

**Previously coated surfaces:** Must be clean and dry. Residual moisture may cause bubbling in the applied **Clearcure** film.

### Specification Notes:

- Number of coats and spreading rate:**  
When coating timber and timber products, the dilution required, spreading rates and the number of coats will depend on the porosity of the surface. On denser surfaces, brush grade may require extra dilution for additional penetration, and on open porous surfaces, spreading rate in at least the first coat will be reduced. Note also where the best possible finish quality is required, intercoat sanding may be needed.
- Dry times:**  
These relate to normal temperature (20-23°C) and humidity (50-60% RH) conditions. In particular, a variation in the humidity will affect through-cure times, with higher humidity shortening the time, and lower humidity prolonging cure time.

### Application Properties:

#### Spreading rate: Brush Grade

Three coat work	Primer	10 sqm/litre
	Bodycoat	12 sqm/litre
	Topcoat	14 sqm/litre
Four coat work	Each coat	14-15 sqm/litre

#### Spreading rate and dilution: High Solids Grade

Three coat work

Primer	Equal volumes Clearcure:Colourcure Thinners 10 sqm/litre of mix.
Bodycoat	3 volumes Clearcure:2 volumes Colourcure Thinners 12-14 sqm/litre of mix.
Topcoat	2 volumes Clearcure:1 volume Colourcure Thinners 14-15 sqm/litre of mix.

#### Dry times:

Dry to recoat	3-6 hours
Intercoat time	4-24 hours
Through cure	24-28 hours (full system)

#### Thinning/Clean Up

Use **Colourcure Thinners** only. Clean equipment immediately after use.

Note: This product cures on exposure to atmospheric moisture. When a new container is opened, its contents should be used as soon as possible, and the container must be tightly sealed at all times when not in use. It is recommended that containers be used within two years of manufacture date.



**Health And Safety:**

Wear barrier cream when handling this material, and cartridge mask plus goggles when spraying or applying in a confined space. DO NOT SMOKE within 20 metres of application/handling area. Keep containers tightly sealed at all times when not in use, and store in a dry, well-ventilated area.

**Transport classification:** UN1263 Class III

**Equus Industries Ltd**  
**PO Box 497**  
**Frankston 3199**  
**Victoria**  
**Phone: 03 9706 6226 Fax 03 9706 4880**  
**Email: [tech-support@equus.com.au](mailto:tech-support@equus.com.au)**  
**Web: [www.equus.com.au](http://www.equus.com.au)**