

# Chevaline Clearglaze

## Gloss or satin overglaze and clear sealer

### Purpose And Areas Of Use:

A clear overglaze for the **Chevaline** product range. To reduce dirt retention and facilitate cleaning in both exterior and interior situations. Also as a clear sealing system for concrete and brickwork to enhance appearance and prevent water penetration. **Clearglaze** should not, however, be regarded as a graffiti-resistant coating.

### Product:

A clear waterborne modified acrylic system with properties of high adhesion, early water resistance and film flexibility combined with toughness. Available in gloss, satin and matt finishes.

### Process Compatibility:

**Clearglaze** is compatible with and can be applied over the following **Chevaline** products.

<b>Coverall-E</b>	<b>Coverall-T</b>
<b>Dexx</b>	<b>Arcutexx</b>
<b>Coverall</b>	

### Colour:

Liquid:	Opaque White
Applied Film:	Clear water-white

### Standard Pack:

4 litre, 15 litre plastic pails.

### Physical Properties:

#### Liquid Material (Concentrate):

Solids (% by volume):	34%
Specific Gravity:	1.05
Flash Point:	None – waterborne system.
Shelf Life:	Three years – original sealed pails when stored in cool dry conditions.

#### Applied Film:

Flexibility:	Passes 3mm mandrel.
Durability:	Excellent long term service may be expected from the coating. During formulation, care was taken to ensure that a coating was produced with excellent UV resistance, wet abrasion resistance, and blister resistance when exposed to soap and water, as well as minimum dirt pick up.

Chemical Resistance: Good resistance against general atmospheric pollutants, domestic cleansers, and normal household pollutants and products. Limited resistance to solvents and oils.

Fungus Resistance: **Chevaline Clearglaze** contains a highly effective anti-fungal preparation which does not contain toxic metals or phenols.

Normal Film Thickness: 20-35 microns per coat.

### Surface Preparation:

Previously coated surfaces (old or new)

1) Surfaces coated with **Chevaline** process listed under "Process Compatibility". Ensure surface is clean and dry. If necessary, use medium pressure water washing to ensure the surface is thoroughly clean. On old surfaces, repair any existing mechanical damage with the same process as before prior to coating.

2) All other surfaces

If the existing coating is now to be a water-based material, and is in sound condition, treat as in (1) above. On all other surfaces, clean and apply a test area of **Chevaline Clearglaze** before proceeding with complete treatment. If doubt exists as to compatibility, alter the specification to include one full coat of **Coverall** or **Covercryn** depending on surface profile.

Brickwork or manufactured stone: Ensure all pointing is sound. Replace missing pointing with a weak (1:4½) cement/sand mortar plasticised with **Chevaline PVA Admix** and allow to cure 7 days minimum before proceeding. Remove all laitance and efflorescence by mechanical means or with a weak acid solution (1:20 muriatic acid:water) followed by copious medium-pressure water washing and allow to dry. If in doubt regarding acid treatment use water washing and scrubbing only, with neutral detergents incorporated in wash water as necessary to remove grime. Ensure all potential water entry points in adjacent surface around opening are well-sealed.

### Priming:

Previously coated surface:

1) Coated with a compatible **Chevaline** process:  
No priming needed.

2) Other Surfaces:

If test patch or surface condition indicates, prime with one coat of **Coverall** at 5 sqm/litre.

Brickwork, Manufactured Stone:

If moisture meter testing indicates presence of moisture (red scales), or its surface has been thoroughly wetted within 96 hours prior to coating, apply one coat of **Clearglaze Penetrant** at approximately 10-12 sqm/litre as a primer sealer.

### Application Method:

**Clearglaze** can be applied by brush, roller, air-assisted or airless spray. It is supplied as a concentrate, and must always be diluted on site with clean tap water prior to application.



Dilution will depend on method and conditions and the figures below are indicative only. It is important that the spreading rates per litre of **Clearglaze** concentrate for a particular surface in "Application Properties" are achieved.

**Brush:** Use a varnish brush on textured surfaces, or "Speedbrush" on smooth surfaces.

**Roller:** Use short nap or foam roller on smooth surfaces.  
Dilution: 4.5-6 litres water/15 litres **Clearglaze** concentrate.

**Air-assisted Spray:** De Vilbiss JGA tip or similar.  
Dilution: 6-9 litres water/15 litres **Clearglaze** concentrate.

**Airless Spray:** 0.22-0.24mm or 9-10 thou tip.  
Dilution: 6-7.5 litres water/15 litres **Clearglaze** concentrate.

Brush/roller application on textured surfaces may require two coats for even coverage. Always use "double-pass" technique when spraying.

#### Application Properties:

Spreading Rate: Will vary depending on surface profile and porosity. The aim is to achieve a continuous film with consistent finished appearance. The following rates are a guide, based in concentrate as supplied by Equus.

Smooth, previously coated surfaces:  
11-12 sqm/litre (165-180 sqm/15L pail) in one coat.

Textured previously coated surfaces:  
Brush/roller 12-15 sqm/litre (180-225 sqm/15L pail) per coat in two coats.

Textured previously coated surfaces:  
Spray 9-11 sqm/litre (135-165 sqm/15L pail) in one coat.  
Overglaze for **Chevaline Dexx**  
10 sqm/litre (150 sqm/15L pail) in one coat.  
On Brick etc.  
8-15 sqm/litre (120-225 sqm/15L pail) in at least two coats.

Dry time:

Touch dry	1-2 hours
Through dry	2-4 hours
Dry to recoat (self texture)	1-2 hours
Trafficable (on <b>Dexx</b> )	24 hours

All under normal conditions of 18-23°C and 60-70 % R.H. Cooler damper conditions prolong dry times. Do not apply **Clearglaze** in air temperatures less than 8°C or when the surface temperature is less than 5°C.

Clean up/Thinning: Use clean tap water. Clean gear immediately after use - dried **Clearglaze** can prove difficult to remove.

#### Specification Notes:

**Chevaline Clearglaze** can be used in three distinct ways.

- 1) As an overglaze for **Chevaline** wall finishes to inhibit dirt retention and facilitate cleaning.
- 2) As a clear topcoat for **Chevaline Dexx** membranes to improve appearance and cleanability.

- 3) As a clear sealer for brickwork or manufactured stone to prevent water entry and improve appearance.

Specifications for the first two applications above are easily written by incorporating the following sentence within the body of the process specification. "The applied process shall include a final coat of **Chevaline Clearglaze** gloss/satin (delete one) finish applied by the Contractor in accordance with the Manufacturer's directions specific to the end use."

For the third application, there may be considerable variation in the number of coats, type of finish and application method depending on the quality of brick or manufactured stone. We recommend that any specification for this use should be based on application of a trial sample, either on site (for existing surfaces) or on representative surfaces (for new construction). To cover this the following clause can be used in tender documents or schedules.

"The surface indicated in (nominate document or plan number), shall be sealed against water penetration for ease for cleaning (delete inappropriate item) with **Chevaline Clearglaze** using appropriate preparation and priming techniques and application methods to duplicate the appearance and performance of the approved sample. The finish shall be gloss/satin (delete one) in appearance. All preparation of the surface and application of materials shall be carried out by an Approved Equus Contractor working in accordance with information and guidelines provided by the Manufacturer.

#### Maintenance:

Depending on end use, **Chevaline Clearglaze** will require recoating periodically. This may vary in the time from 3 years on well-trafficked Dexx to 10+ years as a wall coating glaze. Recoating should be timed to occur before damage is caused to the underlying coating of surface. Simply wash with weak neutral detergent solution, rinse and dry prior to recoating. If existing surface is scored, lightly sand these areas and rinse again - then recoat.

#### Warranties:

When **Chevaline Clearglaze** is used as a topcoat only, any warranty applicable will be the warranty for the whole system that has been applied. In situations where **Clearglaze** is applied as a sealing process for brick or manufactured stone, no warranty is normally given. No warranty of graffiti-resistance should be made or implied for any **Clearglaze** coated surface.

#### Health and Safety:

**Chevaline Colourglaze** is a waterborne material and contains no mammalian toxic substances. It is non-flammable and requires no special storage conditions other than protection from frost. However, we recommend the use of barrier cream on hands and safety spectacles when handling/applying this material and the use of cartridge mask when spraying in confined spaces with poor ventilation. Equus Safety Class 1.

**Shipping restrictions:** None