

Chevaline Coverall-T

Roller Texture

High-Build Rounded Texture Coat

Purpose & Areas Of Use:

A high build rounded roller texture finish, for use in all interior and exterior situations. **Coverall-T** can be applied to all stable building materials over an appropriate primer and finished with one of a range of topcoats depending on service conditions. Particularly suited for use in public areas because of cleanability and surface uniformity.

Colour:

Available in Australian Standard 2700-1996 colours. Can be tinted to match other colours on demand.

Product:

A filled thixotropic waterborne acrylic material. Is tough and durable with high adhesion, fast drying and has early water resistance.

Process Compatibility:

Use with **Coverall Primer Sealer**, **Blockfil** or **Coverfil** primers depending on surface to be coated.

The following **Chevaline** topcoats can be used to overcoat **Coverall-T**:

Covercyl	Colourglaze	Stonewash
Coverall	Extracover	Earthen
Colourcure	Exterior Lo-Sheen	

Standard Pack:

15 litre plastic pail

Physical Properties:

Liquid Material (Concentrate):

Solids (% by volume): 49%
 Specific Gravity: 1.3
 Flash Point: None – waterborne system.
 Shelf Life: Three years – original sealed pails when stored in cool dry conditions.

Applied Film:

Flexibility: Passes 5mm mandrel.
 Durability: Very good weather resistance. System life depends on topcoats selected for use.

Adhesion: Excellent adhesion to recommended primers.

Chemical Resistance: Very good to normal atmospheric pollutants. System resistance will depend on topcoat properties.

Fungus Resistance: **Coverall-T** contains an effective mould resistant additive which contains no toxic metals or phenols.

Surface Preparation:

All surfaces must be clean, dry and continuous at the time of coating application. In exterior situations waterblast surface if practical and/or necessary to remove existing loose paint, surface dirt and unsound material. All interior building boards shall be fixed, taped and stopped according to board makers instructions. All masonry block surfaces shall be de-nibbed and/or patched using **Chevaline Troweltexx**, and neatly tuck or flush pointed as required. When moving joints are to be installed refer to Equus for advice on the particular application and circumstances. Cellulose fibre-cement joints shall be taped according to instructions provided to Approved Equus Contractors, and approved by the board manufacturers.

Priming:

Fibrement boards, cement plaster and “tight” concrete surfaces: **Coverall Primer Sealer** applied by brush at 9-10 sqm/litre. **Masonry block and “open” off-form concrete:** **Blockfil** or **Coverfil**. Primer type and spreading rate at 3-5 sqm/litre dictated by surface profile. **Plaster board:** **Chevaline Epistixx Primer** applied by brush or roller at 8-9 sqm/litre.

Application Properties:

Spreading rate: 1.2-2.0 sqm/litre (18-30 sqm/15L pail) depending on texture required.

Dry times:

Touch dry	2-3 hours
Through dry	2-24 hours
Full Hardness	7-10 days
Under normal conditions	

Recoat times:

Waterborne topcoats	8-12 hours
Solventborne topcoats	24-48 hours allow up to 72 hours in winter.

Roller type:

Use a GoopLoop or Blacktex roller sleeve to achieve correct profile. On large areas use two rollers - one to apply and one to even out the texture.

**Specification Notes:**

1. The normal specification for **Coverall-T** is Standard Specification P2021 which incorporates the material as part of a 3-4 coat system.
2. While masking is still in place the appropriate **Chevaline** Topcoat(s) shall be applied. Advice can be sought from the Manufacturer as to an appropriate topcoat for the likely service conditions.

Maintenance:

Topcoats should be checked for recoating on a 7-10 year cycle for exterior use and 10-12 year cycle for interior use. Clean when required using low-medium pressure spray and a dilute neutral detergent solution. If topcoats are renewed whilst film is still sound, the life of the system will be easily prolonged for further similar cycle periods.

Health And Safety:

Wear barrier cream when handling this material.

Equus Industries Ltd
PO Box 497
Frankston 3199
Victoria
Phone: 03 9706 6226 Fax 03 9706 4880
Email: tech-support@equus.com.au
Web: www.equus.com.au