

# Chevaline Epistixx Topcoat

## Glossy waterborne epoxy finish coat

### Purpose & Areas Of Use:

A glossy waterborne epoxy finish coat for use on most stable building surfaces. It may be used as an easy to clean hygienic wall finish or as a medium duty floor finish, generally in interior situations.

It is ideal for use in situations where solvent release during application is not desirable.

### Product:

A pigmented two component, waterborne epoxy coating based on a modified epoxy resin and polyaminoamide curing agent combination.

### Process Compatibility:

Exhibits excellent adhesion to most building materials primed with **Chevaline Epistixx Primer**.

### Colour:

Near match to requirement. Some mid and deep tone colours may be subject to minimum order quantities and/or colour surcharge.

### Standard Pack:

1,4,8,5 batch units. Units A and B are both packed in plastic pails.

### Physical Properties:

Liquid Material:	Unit A	Unit B	Mixed
Solids Volume	96.5%	31.9%	58%
Specific Gravity	1.96	1.05	1.42
Flash Point	>100°C	—	—
Shelf Life	3 years	2 years	
Appearance	Pigmented	Clear Brown	

### Applied Coating:

Wear resistance: Excellent

### Chemical Resistance:

Fresh water	Excellent
Brine and salt	Excellent
Fuels and greases	Excellent
Petrol and Hydrocarbon solvents	Excellent
Caustic soda 10%	Very good
Inorganic acids	Fair to poor
Organic acids	Not recommended
Suitable for potable water applications	

Consult Manufacturer for specific advice where necessary.

### Surface Preparation:

Concrete, plaster, previously painted surfaces, fibre cement board, stone, slate and tiles must be primed with **Chevaline Epistixx Primer**. The primed surface must be free of all contaminants prior to the application of the topcoat.

Steel should be clean and primed with **Protexx Zincure**.

### Application Method:

Units A and B for each batch should be thoroughly mixed by adding A to B, drill mixing for 4-5 minutes until completely homogenous. The mixed material should then be diluted with up to 30% by volume of clean water, mixed and allowed to stand 10 minutes before using. Application may be by brush, roller or spray (airless spray preferred).

### Application Properties:

#### Spreading rate:

Walls	8-10 sqm/litre/coat
Floors	7-8 sqm/litre/coat

All rates are per litre as supplied. Normal d.f.t. for a two coat finishing system is between 120-165 microns.

Pot life	1.5-2 hours
Dry time	4-8 hours dry/recoat 24-48 hours (15°C, 60% RH)
Cure time	7-10 days for full cure. Note that low temperatures and/or high humidities will considerably retard cure time. Do not apply in temperatures below 5°C or relative humidity greater than 85%.

**Thinning/Clean Up:** Thin with clean tap water. Clean gear by rinsing with water and wiping with Xylol.

### Specification Notes:

- Although **Chevaline Epistixx Topcoat** is waterborne allow adequate ventilation, not so much for safety reasons as to ensure adequate intercoat/drying occurs.
- Although mainly designed for interior use, it may on occasion be used in exterior situations. However, as an epoxy coating it will be subject to chalking and light colours will yellow slightly when exposed to exterior conditions, particularly ultra violet light.



161  
2 pages

PRODUCT  
DATA  
SHEET

**Health And Safety:**

Wear barrier cream when handling **Chevaline Epistix Topcoat** to prevent epoxy sensitisation and possible dermatitic effects. Always store above 0°C to prevent possible deterioration in the unmixed components. Do not smoke while handling the materials.

**Transport Classification:** Unit A - no restrictions  
Unit B - no restrictions

**Equus Industries Ltd**  
**PO Box 497**  
**Frankston 3199**  
**Victoria**  
**Phone: 03 9706 6226 Fax 03 9706 4880**  
**Email: [tech-support@equus.com.au](mailto:tech-support@equus.com.au)**  
**Web: [www.equus.com.au](http://www.equus.com.au)**