

Keim Restauro[®] Gieb

Casting Mortar

Natural Stone Replacement

Product description

Mineral dry bagged restoration mortar with hydraulic binders.

Field of application

KEIM Restauro-Gieß is a natural stone replacement material for the reinstatement of stone architectural details and figures by open or closed form casting.

Product properties

Material characteristics acc. to WTA leaflet 3-11-97/D

Bulk density:	approx. 1.55 g/cm ³
Water consumption:	approx. 0.17 l/kg
Working time:	at most 45 min
Setting time:	> 8 h
Compressive strength:	approx. 42 N/mm ²
Bending tensile strength:	approx. 9 N/mm ²
Modulus of elasticity:	approx. 26,0 KN/mm ²
Thermal dilatation:	approx. 5 X 10 ⁻⁶ (1/K)
Hygic dilatation:	0.9 mm/m

Colour shade

Standard shades in accordance with natural stone colour swatches or special shades to match stone sample. All shades can be mixed with one another. Colour shades are adjusted for cast surfaces which have not been further finished. Slight variations in shade due to differing setting conditions cannot be ruled out.

Packaging

30 kg sacks

Application instructions

Application temperature

Ambient und substrate temperature must not fall below +5°C.

Mixing

KEIM Restauro-Gieß is mixed with water only, approx. 5 L per 30 kg. Use a mixer or compulsory mixer for larger quantities. After a maturing period of 5 minutes, the mortar should flow readily.

Casting

Silicone rubber moulds are used for reproducing shapes. At least 48 hours must elapse before removing the casting from the mould.

Finishing

At least 8 days must elapse before finishing using masonry techniques is possible. It should be noted that such work generally results in a lighter colour shade.

Consumption

Approx. 2.2 kg/l

Cleaning of tools

Clean with water immediately after use.

Storage

12 months in a closed sack under dry conditions.

Hazardous substances

Xi	Irritant
R38:	Irritating to the skin.
R41:	Risk of serious damage to eyes.
S2:	Keep out of reach of children.
S22:	Do not breathe dust.
S24/25:	Avoid contact with skin und eyes.
S26:	In case of contact with eyes, rinse immediately with plenty of water und seek medical advice.
S37/39:	Wear suitable gloves und eye/face protection.
S46:	If swallowed, seek medical advice immediately und show this container or lable.

Transport hazard class

Not applicable

Disposal

EC Waste Code no. 17 01 01

Any residues must be emptied out of sacks before recycling.

Solidify any residual material with water and, after consulting the relevant authorities, dispose of in a building material landfill site.

Safety instructions

Provide appropriate protection for surfaces which are not to be treated. Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with plenty of water.

Protect the eyes and skin from splashes. When using, do not eat, drink or smoke. Keep out of reach of children.

Low on chromate according to TRGS 613

Equus Industries Ltd

PO Box 497

Frankston 3199

Victoria

Phone: 03 9706 6226 Fax 03 9706 4880

Email: tech-support@equus.com.au

Web: www.equus.com.au