

# Chevaline Skimflush

## *Elastomeric, surface filling, flushing paste*

### Areas of Use:

As a surface filler/flashing paste for use over Superfil 2000 filled joints.

### Product:

An elastomeric, high solids, waterborne acrylic thin film filler formulated for application by broadknife or trowel.

### Process Compatibility:

Chevaline Skimflush adds a proprietary finish, is compatible with all Chevaline High Build water-based coatings including:

Troweltexx 2000	Coverall-T
Coverflexx	Covertexx
Arcutexx	Spraytexx G

### Colour:

Off white

### Standard Packs:

10 litre plastic pails

### Physical Properties:

#### Liquid Material:

Volume solids:	66%
Weight solids:	88%
Specific gravity:	1.3-1.35
Flash point:	None - waterborne system
Shelf life:	Two years in original sealed containers

#### Applied Material:

Extension capability: As a lap sealing film the maximum extension of a film at nominal thickness of 0.5mm is 300% at 21°C.

Durability: When over-coated with a compatible Chevaline product the excellent Flexibility of and elasticity properties will be maintained in excess of the life of the topcoat.

Adhesion: Excellent to Superfil 2000 and most common building materials. New and porous surfaces may require a primer.

Chemical resistance: Resistance to all normal environmental pollutants. However do not use as an uncoated chemically resistant sealant.

Fungus resistance: Chevaline Skimflush contains a highly effective mould-resistant additive which does not contain toxic metals or phenols.

### Surface Preparation:

Ensure that the Chevaline Superfil 2000 to be overcoated is clean and dry.

### Priming:

Not required when used over Chevaline Superfil 2000. For all other surfaces, refer to Equus Industries Ltd.

### Application Procedure:

Skimflush is a paste-like material best applied by broadknife, trowel, spatula or putty knife.

### Application Properties:

#### Spreading rate:

As a skim film applied to fill imperfections in a Superfil 2000 application a spreading rate of 10-15 lineal metres will be achieved depending upon the surface finish achieved with the Superfil 2000 (i.e. 100-150 lineal metres per 10 litre pail).

#### Dry time:

Touch dry:	1.5-2 hours
Full through dry:	3-7 days (depending upon application thickness)

**Note:** Do not apply in air temperatures less than 8°C or when surface temperature is less than 5°C.

#### Recoat time:

With waterborne Chevaline coatings 8-24 hours

**Note:** Normal drying conditions for times given above are 18-23°C and 60-70% R.H.

#### Clean up:

Clean equipment immediately after use with clean water.

#### Health & Safety:

Chevaline Skimflush is a waterborne material and contains no mammalian toxic substances. It is non-flammable and requires no special storage conditions other than protection from frost or heat greater than 30°C for extended periods.

Wear barrier cream when handling Skimflush intermittently and protective gloves with prolonged use.

**Equus Industries Ltd**  
**PO Box 497**  
**Frankston 3199**  
**Victoria**  
**Phone: 03 9706 6226 Fax 03 9706 4880**  
**Email: tech-support@equus.com.au**  
**Web: www.equus.com.au**