

Chevaline Spraytexx Natural

Sprayed Texture

Interior/exterior texture finish

Purpose & Areas Of Use:

A high build aggregate filled sprayed texture finish, for use in all interior and exterior situations. Sprayed aggregate effect can be varied to suit aesthetic and service requirements. **Spraytexx Natural** can be applied to all stable building materials over appropriate primer and finished with an appropriate Glazecoat depending on service conditions and aggregate enhancement required.

Product:

A natural coloured aggregate-filled thixotropic waterborne acrylic material. Is tough and durable with high adhesion, fast drying and early water resistance.

Process Compatibility:

Use with **Coverall Primer Sealer, Blockfil, Coverfil or Epistix** primers depending on surface to be coated, with **Coverall Bodycoat** in all cases.

The following **Chevaline** Glazes can be used over **Spraytexx Natural**: **Clearglaze, Chemglaze, Clearcure.**

Colour:

Available in enhanced natural aggregate colours. Colour will depend on the blend of aggregates used.

Standard Packs: 15 litre plastic pail.

Physical Properties:

Liquid Material:

Solids (% by volume): 75%
Specific Gravity: 1.5 - 1.55
Shelf Life: Two years in original sealed pails when stored in cool, dry conditions.

Applied Coating:

Flexibility: Passes 10 mm mandrel.
Durability: Very good weather resistance. System life depends on glazecoats selected for use.
Adhesion: Excellent adhesion to recommended primers.
Chemical Resistance: Very good to normal atmospheric pollutants. System resistance will depend on topcoat properties.
Fungus Resistance: **Spraytexx Natural** contains an effective mould resistant additive which does not contain toxic metals or phenols.

Surface Preparation:

All surfaces must be clean, dry and continuous at the time of coating application. In exterior situations waterblast surface if practical and/or necessary to remove existing loose paint, surface dirt and unsound material. All interior building boards shall be fixed, taped and stopped according to board makers instructions. All masonry block surfaces shall be de-nibbed and/or patched using **Chevaline Troweltexx**, and neatly tuck or flush pointed as required. Where moving joints are to be installed refer to Equus for advice on the particular application and circumstances.

Cellulose fibre/Hardiflex joints shall be taped according to instructions provided to Approved Equus Contractors.

Priming:

Hardiflex boards, cement, plaster and "tight" concrete surfaces: **Coverall Primer Sealer** applied by brush at 9-10 sqm/litre.

Use **Epistix** on critical surfaces at 9-10m²/litre. Masonry block and "open" off-form concrete: **Blockfil** or **Coverfil** Primer type and spreading rate at 3-5 sqm/litre dictated by surface profile.

Gypsum plaster board: **Chevaline PBT Primer** applied by bush or roller at 8-9 sqm/litre.

Bodycoat:

On all surfaces apply **Chevaline Coverall** at 2.5-3.0 sqm/litre as a waterproof background and allow to dry overnight.

Application Properties:

Spreading rate:	0.5-0.6 sqm/litre (7.5-9 sqm/15l pail)	depending on texture required.
Dry times:	Touch dry 1-2 hours Through dry 12-24 hours Full hardness 7-10 days Under normal conditions	
Recoat times:	Waterborne topcoats 8 - 12 hours Solventborne topcoats 24 - 48 hours	
Spray setup:	allow up to 72 hours in winter. Hopper gun or mono-pump texture gun air pressure 20-30 p.s.i. Nozzle size 4-8mm dia. depending on required texture.	



213
2 pages

PRODUCT
DATA
SHEET

Specification Notes:

1. **Spraytexx Natural** is not generally recommended in areas of high industrial pollution fallout where the highly textured surface may retain unsightly pollutants and dirt.
2. While masking is still in place an appropriate **Chevaline Glaze** shall be applied. Advice should be sought from the Manufacturer as to the appropriate glaze for the service conditions. Normally **Clearglaze** shall be used.

Health And Safety:

Wear barrier cream when handling this material. Goggles or safety glasses should be worn while spraying is in progress.

Equus Industries Ltd
PO Box 497
Frankston 3199
Victoria
Phone: 03 9706 6226 Fax 03 9706 4880
Email: tech-support@equus.com.au
Web: www.equus.com.au