

# Traxx 2000 Wearcoat

## Elastomeric roof and deck topcoat (smooth or non-skid)

### Key Benefits Summary:

- Formulated for maximum exterior durability.
- Very good resistance to cleaning chemicals and chemical splashes.
- Easy to maintain and recoat if damaged.
- Gloss level can be varied to suit end use.

### Limitations:

- Bright colours may require additional coats for full opacity
- May be slow curing under adverse circumstances.
- Has a low film build - it is designed as a topcoat only for elastomeric membrane systems.

### Colour:

Available in Australian Standard 2700-1996 colours. Can be tinted to match other colours on demand.

### Standard Pack:

1 and 4 litre units (prebatched)

### Physical Properties:

Liquid Material:	Unit A	Unit B
Solids (% by volume):	49%	47%
Specific Gravity:	1.25	1.01
Flash Point:	32°C	32°C
Shelf Life:	3 years	2 years

### Applied Film: (Traxx 2000 with Wearcoat)

Flexibility: Passes 3mm mandrel @ 500µ d.f.t.

Elongation: >250% at break

Tear Strength: >3.5N/mm

Durability: Excellent.

Adhesion: Very good with correct priming system

Chemical Resistance: Excellent resistance to treated and waste water. Dilute acids and alkalis, salts etc. general process wastes.

Abrasion Resistance: Excellent.

### Surface Preparation:

All surfaces must be clean and dry at time of application. For most applications priming is not mandatory ie.

Porous surfaces: **Traxx Primer 1070** at 10sqm/litre

Dense concrete: **Traxx Primer 1050** at 10sqm/litre  
Contaminated, previously painted & timber surfaces:

**Chevaline Epistixx** at 8sqm/litre

**Protexx Zincure** at 12sqm/litre

Steel:

### Specification Notes:

Refer to individual **Traxx 2000** system specifications for full details.

### Areas Of Use:

A liquid-applied trafficable elastomeric topcoat (smooth or non-skid) for use on roofs, decks, pool surrounds and walkways.

### Product:

A two-component solvent-borne flexible aliphatic polyurethane lacquer available in either smooth or non-skid finish, depending on service conditions.

### Application Properties:

#### Spreading rate: (per coat)

Theoretical: 12.25m<sup>2</sup>/litre (40µ dft) - smooth

Practical: 10m<sup>2</sup>/litre (40µ dft) - smooth

8m<sup>2</sup>/litre - non slip

### Recommended film build:

Reinforced systems 35-40 µ / coat

Unreinforced systems 35-40 µ / coat

### Dry time:

Touch dry 2-6 hours

Through dry 8-20 hours

Pot life: 4-8 hours

Thinning/Clean up: Colourcure AP Thinners

### Application Method:

Mix unit B into unit A, ensuring complete homogeneity (3-4 minutes with a drill and beater). Apply direct from mixed can by brush, roller or spray. Thin with **Colourcure AP Thinners** as needed for easy spreading.

### Health And Safety:

These materials are solvent-based urethane coatings. All normal precautions for handling solvent-borne materials must be observed including:

- Storage in cool dry conditions away from naked flames.
- No smoking in area while handling or applying Traxx 2000 Wearcoat.
- Use barrier cream on exposed skin.
- Use of solvent cartridge mask and safety goggles while handling material.

Note that these materials contain less than 0.2% free isocyanate monomer and presents a low health hazard, but in some countries special regulations may pertain.

### Transport Classification:

UN No. 1263

IMW Classification 3.3

Equus Industries Ltd

PO Box 497

Frankston 3199

Victoria

Phone: 03 9706 6226 Fax 03 9706 4880

Email: [tech-support@equus.com.au](mailto:tech-support@equus.com.au)

Web: [www.equus.com.au](http://www.equus.com.au)